

PRIMAPAGE NEW ivory

Specification sheet



Primapage is a thin opaque uncoated paper dedicated to monochrome printing in either heat set or cold set. The combination of its natural brightness, excellent opacity, the low level of strike through plus a silky touch provides a finished publication which is “easy on the eyes”. Primapage is available in both reels and sheets.

FSC® or PEFC certified on request

Specifications										
Characteristics	Unit	Standard								
Code			PPN29I17	PPN31I17	PPN34I17	PPN39I17	PPN45I17	PPN50I17	PPN55I17	PPN60I17
Grammage	g/m ²	ISO 536	29 g/m ²	31 g/m ²	34 g/m ²	39 g/m ²	45 g/m ²	50 g/m ²	55 g/m ²	60 g/m ²
Basis weight (USA)	lbs	24*45/500	19,6	21	23	26,4	30,4	33,8	37,2	40,5
Thickness	µm	ISO 534	33,9	36,3	39,8	45,6	52,7	58,5	64,4	70,2
Bulk	cm ³ /g	-	1,17	1,17	1,17	1,17	1,17	1,17	1,17	1,17
PPI (indicative)	pages/inch	T 411	1554	1428	1286	1124	966	880	798	720
Opacity	%	ISO 2471	80	81,5	81,5	84	85	87	88,5	90
Absolute humidity	%	NF Q03-003	5,7							
Permanent paper	-	ISO 9706	YES							
Optical brightner	-	-	NO							

Paper tolerances	
Grammage: nominal value + / - 1 g/m ²	ISO whiteness minimum: nominal value 1 point
Thickness: + / - 2 µm	ISO opacity minimum: nominal value 1 point
PPI (indicative)	Absolute humidity: + / - 0.5%

Finished goods tolerances
Joins: maximum of 2 joins per reel with at least 60% of the reels being “join free”
Width: customer width - 0 mm, + 2 mm
Outer diameters of 100 cm, 114 cm or 120 cm: - 3 cm, + 2 cm

Minimum making: Quantity required by the mill will be dependent on both the production schedules and the possibilities at the time of the order for a combination of widths to cover the machine deckle. Please contact your sales representative for more details.

Measurements made on Jumbo rolls according to the Standards and Norms in place at that time.

Validated: July 2020

Qualified by Hervé Brunet-Jailly - Product Manager